

# TEST RESULTS

Table 1: Estimated LIDTs for sample OPPN503.

Test mode	Threshold
1-on-1	0.378 $^{+0.021}_{-0.020}$ J/cm <sup>2</sup>
10-on-1	0.348 $^{+0.021}_{-0.020}$ J/cm <sup>2</sup>
10 <sup>2</sup> -on-1	0.325 $^{+0.020}_{-0.020}$ J/cm <sup>2</sup>
10 <sup>3</sup> -on-1	0.286 $^{+0.017}_{-0.017}$ J/cm <sup>2</sup>

## CHARACTERISTIC DAMAGE CURVE




Figure 2: Characteristic damage curve.