

LIDT TEST RESULTS

CHARACTERISTIC DAMAGE CURVE

Table 1: Estimated LIDTs from fitting model for sample P11.

Test mode	Threshold (catastrophic)
1-on-1	$0.881^{+0.035}_{-0.034} \text{ J/cm}^2$
10-on-1	$0.836^{+0.032}_{-0.032} \text{ J/cm}^2$
10^2 -on-1	$0.819^{+0.032}_{-0.032} \text{ J/cm}^2$
10^3 -on-1	$0.798^{+0.031}_{-0.030} \text{ J/cm}^2$
10^4 -on-1	$0.779^{+0.029}_{-0.029} \text{ J/cm}^2$
10^5 -on-1	$0.779^{+0.029}_{-0.029} \text{ J/cm}^2$




Figure 2. Characteristic damage curve.